

Styrene acrylate dispersion for use with tile adhesives, levelling compounds and **weber.sys protect**

## weber PR360

New improved



### About this product

**weber PR360** is a priming solution for the preparation of most substrates prior to the application of tile adhesives, levelling compounds and **weber.sys protect** tanking system. It offers good alkali resistance and adhesion properties in both wet and dry environments.

### Technical data

Working time (pot life)	N/A
Relative density	1.04
Solids content	49%
pH	8
Colour	White

### Coverage

Substrate	Primer:Water ratio	Coverage (litres/m <sup>2</sup> )
Concrete	1:3	0.10
Porous concrete	1:3 – 1:5	0.20 – 0.40
Ceramic or stone tiles	1:1	0.20
Vinyl	1:1	0.15
Timber or steel	5:1	0.20

### Application properties

Application temperature	Between +10°C and +35°C
Drying time	1 – 5 hours

**Note:** times quoted are at 20°C and are reduced by heat and good ventilation and extended at low temperatures.

### Uses

- Priming substrates prior to the application of:
  - tile adhesives
  - levelling screeds
  - weber.sys protect** tanking system
- Priming porous and non-porous substrates
- Priming internal screeds, concrete and blockwork
- Prime and seal the surface of anhydrite screeds and plaster walls
- Suitable for concrete, anhydrite, plaster, wood, stone, vinyl, steel etc

### Constraints

Do not use:  
 on surfaces that are either wet or frozen;  
 at temperatures below 10°C;  
 if the relative humidity is above 70%.

### Features and benefits

- ▲ Manufactured under BSI Quality Assurance Scheme ISO 9001
- ▲ Regulates the porosity of surfaces prior to the application of adhesive or levelling compound
- ▲ Reinforces the cohesion of the substrate's surface and improves the adhesion of mortars
- ▲ Reduces bubbling and aids flow of levelling compounds

### EU VOC regulations 2008

**EU limit for weber PR360 (cat A/g):** 50 g/l (2007)/30 g/l (2010).  
**weber PR360** contains <15 g/l VOC.

# weber PR360

## Preparation

Surfaces must be clean, dry, sound and free from dust, grease, wax, etc.

Remove any friable residues (peeling paint, old adhesive for vinyl tiles, laitance, etc).

## Mixing

**weber PR360** should be diluted with clean water according to the ratios given.

To obtain the correct mix ratio, always measure the water into a plastic container and add the concentrated primer. The solution should be mixed gently before use.

## Application

**Do not apply weber PR360 onto surfaces that are either wet or below a temperature of 10°C.**

Apply an even coating at a regular thickness with a wool roller or a flat paint brush. Complete coverage of all surfaces is essential.

Clean all tools immediately after use with water.

Drying takes between 1 and 5 hours at +20°C. **weber PR360** must be dry before re-coating.

## Packaging

**weber PR360** is supplied in 1 kg and 5 kg plastic bottles.

## Coverage

See *Technical Data* section overleaf.

## Storage and shelf life

When stored airtight in a cool, dry place at temperatures above 5°C and protected from frost, shelf life is 12 months from date of manufacture.

## Health and safety

Essentially not hazardous.

Not harmful during normal use.

After contact with skin, wash immediately with plenty of water.

In case of contact with eyes, rinse immediately with plenty of water and seek medical advice.

Keep out of the reach of children.

**For further information, please request the Material Safety Data Sheet for this product.**

### Technical services

**Weber's** Customer Services Department has a team of experienced advisors available to provide on-site advice both at the specification stage and during application. Detailed specifications can be provided for specific projects or more general works. Site visits and on-site demonstrations can be arranged on request.

#### Technical helpline

Tel: 01525 722137  
Fax: 01525 718988

### Sales enquiries

**Weber** products are distributed throughout the UK through selected stockists and distributors. Please contact the relevant Customer Services Team below for all product orders and enquiries.

#### England and Wales

Tel: 08703 330070  
Fax: 01525 718988

#### Scotland, Northern Ireland, Isle of Man, Republic of Ireland

Tel: 028 9335 2999  
Fax: 028 9332 3232

#### Saint-Gobain Weber Ltd

Dickens House, Enterprise Way, Maulden Road, Flitwick, Bedford MK45 5BY, UK  
Tel: 08703 330070 Fax: (01525) 718988 e-mail: mail@netweber.co.uk

To the best of our knowledge and belief, this information is true and accurate, but as conditions of use and any labour involved are beyond our control, the end user must satisfy himself by prior testing that the product is suitable for his specific application, and no responsibility can be accepted, or any warranty given by our Representatives, Agents or Distributors. Products are sold subject to our Standard Conditions of Sale and the end user should ensure that he has consulted our latest literature.